

TEST REPORT

BEA250284

Date of report: 2025-02-17

page 1 of 2

Client: Control Union Certifications Germany GmbH

Address: Bornitzstraße 73-75, 10365 Berlin, GERMANY

Order: Fuel testing according ENplus® certification program of wood pellets ENplus® ST.1001:2022

Order date: 2024-12-23; PRJ:853789

Receipt of samples: 2025-02-04

Sample(s): 6 mm wood pellets; "PL 049"





Testing period: 2025-02-05 – 2025-02-14

Sample details: 15 kg pellets in plastic bag class A1 "6mm/MAXIMER/2024-UN"; internal sample no.: BEA250284

BEA250284			result	
parameter ENplus®	limit values A1	limit values A2	6mm/MAXIMER/2024-UN	unit
diameter	6 ± 1, 8 ± 1	6 ± 1, 8 ± 1	6,1	mm (ar)
length (3,15 ≤ L ≤ 40 mm)	(3,15 ≤ L ≤ 40)	(3,15 ≤ L ≤ 40)	13,6 ± 5,5	mm (ar)
length (40 ≤ L ≤ 45 mm)	≤ 1	≤ 1	0,1	%in mass (ar)
length (> 45 mm)	0	0	0,0	piece(s)
amount of pellets for length	≥ 100	≥ 100	1 414	piece(s)
moisture content	≤ 10,0	≤ 10,0	6,3	%in mass (ar)
ash content	≤ 0,70	≤ 1,20	0,32	%in mass (db)
mechanical durability	≥ 98,0	≥ 97,5	98,0	%in mass (ar)
bulk density	600 ≤ BD ≤ 750	600 ≤ BD ≤ 750	670	kg/m³ (ar)
particle density	-	-	1,29	g/cm³ (ar)
coarse fines (3,15 ≤ CPF < 5,6	-	-	0,9	%in mass (ar)
fines content (< 3,15 mm), bulk	≤ 1	≤ 1	-	%in mass (ar)
fines content (< 3,15 mm), bags	≤ 0,5	≤ 0,5	0,4	%in mass (ar)
net calorific value q _{P,net}	≥ 16,5	≥ 16,5	18,3	MJ/kg (ar)
net calorific value q _{P,net}	≥ 4,6	≥ 4,6	5,10	kWh/kg (ar)
net calorific value q _{P,net}	-	-	19,7	MJ/kg (db)
net calorific value q _{P,net}	-	-	5,48	kWh/kg (db)
gross calorific value q _{V,gr}	-	-	19,9	MJ/kg (ar)
gross calorific value q _{V,gr}	-	-	5,52	kWh/kg (ar)
nitrogen content	≤ 0,3	≤ 0,5	0,09	%in mass (db)
sulphur content	≤ 0,04	≤ 0,04	<0,005	%in mass (db)
chlorine content	≤ 0,02	≤ 0,02	0,005	%in mass (db)
arsenic	≤ 1	≤ 1	<0,5	mg/kg (db)
cadmium	≤ 0,5	≤ 0,5	0,23	mg/kg (db)
chromium	≤ 10	≤ 10	<1	mg/kg (db)
copper	≤ 10	≤ 10	<1	mg/kg (db)
lead	≤ 10	≤ 10	<0,5	mg/kg (db)
mercury	≤ 0,1	≤ 0,1	<0,075	mg/kg (db)
nickel	≤ 10	≤ 10	<1	mg/kg (db)
zinc	≤ 100	≤ 100	8,9	mg/kg (db)
shrinking temperature SST	-	-	1080	°C
deformation temperature DT	≥ 1200	≥ 1100	1450	°C
hemisphere temperature HT	-	-	>1550	°C
flow temperature FT	-	-	>1550	°C

db... dry basis, ar... as received

The test results apply only to the samples investigated. As a rule, they are not the only criteria for assessing the raw material or product in question and its suitability for a specific purpose of application. Test Reports may only be made available to third parties, either free of charge or against payment, if the full wording is given and if the author is expressly named. Unless otherwise indicated, at client's request neither the measurement uncertainty was stated, nor were decision rules agreed. The General Terms and Conditions of BEA Institut für Bioenergie GmbH shall apply as amended.

Further measurement uncertainty was stated, if it was decision rules agreed. The General Terms and Conditions of BERN Institut für Bioenergie GmbH shall apply as amended.		
 	director in charge 	
	DI (FH) Magdalena Wojcik	

TEST REPORT

BEA250284





Date of report:	2025-02-17	page 2 of 2
Client:	Control Union Certifications Germany GmbH	
Address:	Bornitzstraße 73-75, 10365 Berlin, GERMANY	
Order:	Fuel testing according ENplus® certification program of wood pellets ENplus® ST.1001:2022	
Order date:	2024-12-23; PRJ:853789	Receipt of samples: 2025-02-04
Sample(s):	6 mm wood pellets; "PL 049"	Testing period: 2025-02-05 – 2025-02-14
Sample details:	15 kg pellets in plastic bag class A1 "6mm/MAXIMER/2024-UN"; internal sample no.: BEA250284	

testing methods	standard
diameter and length	ISO 17829:2015
moisture content	ISO 18134-2:2017
ash content	ISO 18122:2022
mechanical durability	ISO 17831-1:2015
finer content < 3,15 mm	ISO 5370:2023
net calorific value /gross calorific value	ISO 18125:2017
bulk density	ISO 17828:2015
carbon, hydrogen, nitrogen content	ISO 16948:2015
chlorine, sulphur content	ISO 16994:2016, quantification according to ISO 10304-1:2007
minor elements	ISO 16968:2015, quantification according to ISO 17294-2:2023
ash melting behaviour	ISO 21404:2020, ash preparation at 815°C, oxidizing atmosphere
coarse pellets fines 3,15 < CPF < 5,6 mm	ISO 5370:2023
particle density	ISO 18847:2017

remarks

According to the submitted sampling report, the sampling was performed on the 23.12.2024 by Mrs. Agnieszka Kędziora-Urbanowicz at Maximer Sp. z o.o., Nowa Ruskolęka 49a, 07-305 Andrzejewo, Poland; PRJ:853789

The test results apply only to the samples investigated. As a rule, they are not the only criteria for assessing the raw material or product in question and its suitability for a specific purpose of application. Test Reports may only be made available to third parties, either free of charge or against payment, if the full wording is given and if the author is expressly named. Unless otherwise indicated, at client's request neither the measurement uncertainty was stated, nor were decision rules agreed. The General Terms and Conditions of BEA Institut für Bioenergie GmbH shall apply as amended.

		<p>director in charge</p>  <p>DI (FH) Magdalena Wojcik</p>	
---	---	--	---